



Leghe WCu

Parametri

	Lega WCu 75/25	Lega WCu 80/20
Analisi	W 75% Cu 25% (± 2.0)	W 80% Cu 20% (± 2.0)
IACS (Cond. Elettr. Rel.)	38 % min	34 % min
Densità	14,50 Kg/dm ³	15,15 Kg/dm ³
Resistenza a trazione	1910 MPa	2150 MPa
Resistenza a flessione	706 MPa	736 MPa

Spec. ASTM B702